



High activation, water soluble solder wire

Description:

Interflux® **Aquasol 4018** for SnPb alloys is a solder wire with water soluble flux residue.

It is highly activated for increased wetting on surfaces that are difficult to solder or degraded and oxidised surfaces.

Aquasol 4018 residue must be cleaned. Cleaning is easily done with demi water of 35— 45°C (95°F— 114°F) with or without the aid of a saponifier.

Aquasol 4018 can be used in both hand soldering and automated soldering processes.

Aquasol 4018 solder wire contains halogens and is classified as OR H1 according to IPC and EN-standards.



Products pictured may differ from the product delivered



[Click for Interflux' ecological profile](#)

Key properties

- Water soluble flux residue
- High wetting power on surfaces that are difficult to solder.
- Suitable for automated soldering

Availability

Flux type: IF 4018
Flux content: 2,5% w/w

		diameters (mm)					
alloy	melting point	0,35	0,50	0,70	1,00	1,50	2,00
Sn63Pb37	~ 183°C	•	•	•	•	•	•

Note: other alloys and diameters upon request

• = available • = upon request



Work Instructions

Manual soldering

The advised working temperature is between 320°C and 360°C. For more dense metals like Nickel, the temperature may be elevated to 400°C. The use of a good soldering station is important. Use a soldering station with a short response time and with enough power for your application. Choose the correct soldering tip: to reduce the thermal resistance, it is important to create a large contact area with the surfaces to be soldered. Heat up both the surfaces simultaneously. Slightly touch with the solder wire, the point where soldering tip and the surfaces to be soldered meet (the small quantity of solder ensures a drastic lowering of the thermal resistance). Add subsequently without interruption, the correct amount of solder close to the soldering tip without touching the tip. This will reduce the risk on flux spitting and premature flux consumption!

Post solder residue needs to be cleaned. This can be done with demi water of 35— 45°C (95°F— 114°F) with or without the aid of a saponifier.

Handling

Storage

Store the solder wire in a clean environment at ambient temperature.

Handling

To avoid spool and wire damage, handle package with care.

Safety

Please always consult the safety datasheet of the product.

Packaging

The standard packaging is spool of 500g

Other spool sizes upon request



Test results

Conform EN 61190-1-3(2007) and IPC J-STD-004(A)

Property	Result	Method
Chemical		
flux designator	OR H1	J-STD-004A
	F-SW 25	DIN 8511
	2.1.2	ISO 9454
% halide content	>2%	J-STD-004A IPC-TM-650 2.3.35
Environmental		
SIR test	pass (cleaned)	J-STD-004 IPC-TM-650 2.6.3.3
qualitative corrosion, flux	pass (cleaned)	J-STD-004A IPC-TM-650 2.6.15
electro chemical migration	pass (cleaned)	J-STD-004A IPC-TM-650 2.6.14.1

Trade name: Aquasol 4018 Leaded, Water Soluble Wire

Disclaimer

Because Interflux® Electronics N.V. cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our products should make their own test to determine the suitability of each such product for their particular purposes. The product discussed is sold without such warranty, either express or implied.

Copyright:

INTERFLUX® ELECTRONICS N.V

Latest version of this
document on:

www.interflux.com

